

Product Information Sheet

Product

Vacuum bags

Raw Material

PA/PE

Packaging

Inner: Polyethylene (PE)

Outer: Corrugated board

Field Of Application

The bags can be used safely with all types of food under following conditions:

- any long-term storage at room temperature or below (down to -25 °C)
- Warm keeping at
 - up to 2 hours at a temperature $\leq 90^{\circ}\text{C}$
 - up to 4 hours at a temperature of 80°C
 - up to 9 hours at a temperature of 70°C
 - up to 21 hours at a temperature of 60°C

Low temperatures recommendations

In frozen conditions, plastic generally becomes more brittle due to the low temperatures, which can affect its flexibility. If the film is used in frozen condition, be aware:

- The bag may become less flexible and may crack or tear more easily.
- Freezing can weaken the seal of the film over time. For food packaging, this could lead to freezer burn or moisture loss if the seal breaks or weakens.
- Handle frozen packages gently.

Packaging and Packaging Waste

The product and its packaging comply with all essential requirements set out in Directive 94/62/EC on packaging and packaging waste, as well as the forthcoming Packaging and Packaging Waste Regulation (PPWR), Regulation (EU) 2025/40.

Environmental Aspects

Product

The product consists of 100 % virgin plastic based on fossil sources.

Packaging

DUNI GROUP

P.O. Box 237 | SE-201 22 Malmö | Sweden
Phone +46 40 10 62 00 | Org.No. 5565367488 | Reg.Office Malmö
www.dunigroup.com

Polyethylene is made by refining of mineral oil or natural gas. The polymer consists simply of carbon and hydrogen. The corrugated board box is to a large extent made of recycled fibres.

The corrugated board box is made from wood, which is a renewable resource.

Product Safety

The product fulfils the following:

- Regulation (EC) No 1935/2004 (Framework regulation)
- EU Regulation 2023/2006/EC (GMP)
- EU Regulation 10/2011/EC with amendments, Material and products of plastic produced for contact with food.
- EU Regulation (EU) 2024/3190 on the use of bisphenol A (BPA) and other bisphenols
- Duni manufacturing units are certified according to the international quality system ISO 9001. They have also implemented or will implement the environmental management system ISO 14001.

Storage conditions

Recommended storage conditions: 15°C-25°C in a dry place, away from direct sunlight.

End of Life

Recycling

Collection, sorting and material recovery are all part of the recycling process. Recycling is dependent on local waste handling infrastructure.

The product is a multilayer plastic film composed of polyethylene (PE) and polyamide (PA). In current waste-management systems, such structures are typically not suitable for mechanical recycling within the PE stream. End-of-life handling depends on local collection and treatment systems. Please consult your local waste-management guidelines for market-specific recycling instructions.

Energy Recovery

Incineration facilities for energy recovery are dependent on local infrastructure. Incineration for energy recovery is an alternative when material recovery is not available by recycling.

Validity

This is issued 2026-03-13. It is revised when there is a change in the manufacturing process, in the product or in legislation.