

Product Information Sheet

Product

Trays and bowls (no carbon black used)

Raw Material

Polypropylene (PP)

Packaging

Inner: Polyethylene

Outer: Corrugated board

Field Of Application

The PP-trays are intended for deliveries of individual portions of ready-cooked meals from large-scale households. Multiple use is not applicable as these products are intended as disposable products for single use.

The articles can be used safely with all types of food under following conditions:

	Application	Specific conditions	
		Temperature (°C)	Period food contact
☞	Storage in freezer*	-18 – 0	Very long (>> 10 days)
☞	Storage in fridge	0 – 10	Long (> 10 days) The food itself probably sets the limitation
☞	Storage at room temperature	Max 40	Long (> 10 days) The food itself probably sets the limitation
☞	Keeping warm applications	< 70	< 4 hours
☞	Hotfill & serving temperature	< 121	Immediate use
☞	Microwave oven		Short (< 10 min)
No	Conventional application	< 220	Short (< 2 h)

Heat resistance

Due to natural weakness at high temperatures, the heated products must be handled carefully the first minutes after being taken out of an oven or microwave. As temperature decreased the stiffness will be retained.

Heating will cause shrinkage of the material.

Strength impact*

The product is designed to withstand normal handling in frozen condition, but special care is required when handling the products in cold conditions.

DUNI GROUP

P.O. Box 237 | SE-201 22 Malmö | Sweden
Phone +46 40 10 62 00 | Org.No. 5565367488 | Reg.Office Malmö
www.dunigroup.com

Minimum temperature is -18 °C. As the product becomes brittle at low temperatures, the following recommendations should be followed to avoid damage of the products:

- being frozen, the items have to be handled very careful
- stack the finished products upright in the case and do not over stack the products
- avoid that the products can move and shift in the packaging during transport.

Sealability

Good sealing can be obtained with different kind of seal films. Due to the variety of seal films and applications the sealability should be tested by the end user for best acceptance.

Sealing of Tray/Cover

When sealing the trays through welding, a small amount decomposition product is formed. As always when working with heating and melting materials, an adequate ventilation is very important. In most cases a kitchen fan will be sufficient to evacuate the emissions that may arise.

Packaging and Packaging Waste

The product and its packaging comply with all essential requirements set out in Directive 94/62/EC on packaging and packaging waste, as well as the forthcoming Packaging and Packaging Waste Regulation (PPWR), Regulation (EU) 2025/40.

Environmental Aspects

Product

The product consists of 100 % virgin PP based on fossil sources.

Packaging

Polyethylene is made by refining of mineral oil or natural gas. The polymer consists simply of carbon and hydrogen. The corrugated board box is to a large extent made of recycled fibres.

The corrugated board box is made from wood, which is a renewable resource.

Product Safety

The product fulfils the following:

- Regulation (EC) No 1935/2004 (Framework regulation)
- EU Regulation 2023/2006/EC (GMP)
- EU Regulation 10/2011/EC with amendments, Material and products of plastic produced for contact with food.
EU Regulation (EU) 2024/3190 on the use of bisphenol A (BPA) and other bisphenols

- Duni manufacturing units are certified according to the international quality system ISO 9001. They have also implemented or will implement the environmental management system ISO 14001.

Storage conditions

Recommended storage conditions: 15°C-25°C in a dry place, away from direct sunlight.

End of Life

Recycling

Collection, sorting and material recovery are all part of the recycling process. Recycling is dependent on local waste handling infrastructure.

Polypropylene (PP) can be collected and recycled within established plastic collection and recycling streams. However, the ease and effectiveness of recycling depend on factors such as material type, product composition and in some cases colour. Black plastics coloured with conventional carbon black may not be detectable by NIR sorting systems and can therefore have limited recyclability. For this reason, these products do not contain carbon black.

Local waste-management guidelines should always be consulted for market-specific recycling instructions.

Energy Recovery

Incineration facilities for energy recovery are dependent on local infrastructure. Incineration for energy recovery is an alternative when material recovery is not available by recycling.

Validity

This is issued 2026-01-07. It is revised when there is a change in the manufacturing process, in the product or in legislation.